DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE
"We Test Per Your Request"
336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

June 24, 2026

RHODETEC GmbH
Annaberger Str. 73 | 09111 Chemnitz | Germany

Reference: Laboratory Test Report
Lab Identification No. 68608
Invoice No. 99886

Dear Sir or Madam:

One (1) sample, identified as **Opportunity Number: Opp_0036205 – SiGr 02,** was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

Test Results

Specimen Number	Residual Flame (seconds)	Weight Loss (percent)
1	0.0	3.68
2	0.0	3.89
3	0.0	13.65
4	0.0	15.36
5	4.0	21.42
6	7.0	10.54
7	0.0	3.56
8	0.0	11.24
9	0.0	12.18
10	0.0	2.96
AVG	**1.1**	**9.85**

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE.SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE
"We Test Per Your Request"
336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

September 2, 2026

RHODETEC GmbH
Annaberger Str. 73 | 09111 Chemnitz | Germany

Reference: Laboratory Test Report
Lab Identification No. 69410
Invoice No. 100698

Dear Sir or Madam:

One (1) plastic sample, identified as **Opportunity Number: Opp_0037140 – SiGr 02 with Hem Bar,** was received and tested in accordance with the National Fire Protection Association No. 701, "Flame Propagation of Textiles and Films, 2023 Edition, (Test 2, Flat Configuration)". The results are as follows:

Test Results

Specimen Number	After Flame (seconds)	Residual Flame (seconds)	Char Length (inches)
1	0.0	0.0	9.6
2	0.0	0.0	10.3
3	0.0	0.0	11.2
4	0.0	0.0	10.7
5	0.0	0.0	10.8
6	0.0	0.0	10.1
7	0.0	0.0	10.9
8	0.0	0.0	11.3
9	0.0	0.0	10.2
10	0.0	0.0	11.1

The sample submitted **meets** the minimum requirements of the above standard. The length of char on the individual single flat specimens shall not exceed 17.1 inches. Additionally, no specimen shall continue flaming for more than two (2) seconds after the test flame is removed and no residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

Sincerely,

Brian S. Dement

BSD/pd

DIVERSIFIED TESTING LABORATORIES, INC. SEAL 1975 NORTH CAROLINA

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. UNLESS OTHERWISE SPECIFIED, ALL COMPLIANCE STATEMENTS ARE SIMPLE ACCEPTANCE. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.